## (19) World Intellectual Property **Organization**

International Bureau



## 

(43) International Publication Date 17 February 2005 (17.02.2005)

**PCT** 

## (10) International Publication Number WO 2005/014215 A2

(51) International Patent Classification7:

**B23K** 

(21) International Application Number:

PCT/IB2004/002528

(22) International Filing Date: 6 August 2004 (06.08.2004)

(25) Filing Language:

English

(26) Publication Language:

**English** 

(30) Priority Data: 60/494,610

12 August 2003 (12.08.2003)

- (71) Applicant (for all designated States except US): MAGNA INTERNATIONAL INC. [CA/CA]; 337 Magna Drive, Aurora, Ontario L4G 7K1 (CA).
- (72) Inventor; and
- (75) Inventor/Applicant (for US only): HILL, John, Edward [CA/CA]; 119 Fairview Avenue, St. Thomas, Ontario N5R 4X7 (CA).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

## Published:

without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD OF LASER WELDING COATED MEMBERS

(57) Abstract: There is disclosed a method of laser welding a number of coated metal sheets including the steps of: providing the coated sheets to be joined, and creating a raised region on at least one of the coated sheets. The raised region is formed on a first surface of the metal sheet while the second opposite surface of the sheet remains continuous and uninterrupted. A laser is then applied forming a weld joint where gases produced during the forming of the laser weld escape via the at least one embossment. In an alternative embodiment fine particles may be distributed on the surface of one or both of the sheets of coated metal to introduce a gap for the gases produced during the forming of the laser weld a place to escape. Preferably the fine particles will be zinc dust to maintain the coating between the two sheets to be joined.

